

10			1 7	
М	`AC	hnica		lata•
_		1 1 1 1		Z I I F I F

Issued: Sep.2006

Revision 2: March 2019, Page: 1

EP 1140DV

High Thermal Conductive Epoxy Adhesive

Product Description

EP 1140DV, a two-component, thermal conductive epoxy adhesive, offers excellent electrical insulation characteristics together with low thermal expansion and high chemical resistance. EP 1140 DV demonstrates high adhesion to metals and ceramics

Features & Benefits

- High thermal conductivity
- Low thermal expansion
- Excellent electrical insulation
- RT curing
- High chemical resistance
- Long pot life

Applications

Bonding and sealing

Typical Uncured Physical Properties

Note: The following technical information and data should be considered representative or typical only and should not be used for specification purposes.

Base Resins	Base (A) Hardener (B)	Epoxy Polyamides
Appearance/Color	Base (A) Hardener (B)	black amber
Viscosity @ 25°C, mPa*s, ASTM-D-2393	Base (A) Hardener (B)	Soft paste 5500
Density, g/cm ³ @ 25°C	Base (A) Hardener (B)	2.2 1.0
Mix Ratio (A:B), by vol.		4:1

Mail: <u>info@polymer-g.com</u> http://www.polymer-g.com

Tel.: +972 (0)8 9987931, Fax.: +972 (0)8 9965286



Technical Data:

Issued: Sep.2006 Revision 2: March 2019, Page: 2

EP 1140DV

High Thermal Conductive Epoxy Adhesive

Typical Cured Properties

Note: The following technical information and data should be considered representative or typical only and should not be used for specification purposes.

Color	black
Hardness, Shore D	87
Gel Time (2-3mm layer @ 25°C), min	60-80
Initial Curing @ 25°C, hr	6-8
Final Curing @ 25°C, hr	24
Lap Shear Strength, etched Al, MPa	19
Thermal Conductivity, W/m-K	1.1
Operating Temperature, °C	-40 to 120

Storage	Store products at 18-30°C for maximum shelf life.
Packaging	4:1 50cc dual cartridges
Shelf Life	This product has a shelf life of 12 months in unopened dual cartridges
Limitation of Liability	Except where prohibited by law, Polymer-G and seller will not be liable for any loss or damage arising from the Polymer-G product, whether direct, indirect, special, incidental or consequential, regardless of the legal theory asserted, including warranty, contract, negligence or strict liability.

Tel.: +972 (0)8 9987931, Fax.: +972 (0)8 9965286