

**Technical Data:**

Issued: Nov.2011

Revision 2: July 2018, Page: 1

**EP 140FR/ Hardeners EPC 124/ EPC 520/ EPC 304IP55**

**Product Description** EP 140FR is a highly filled potting and encapsulating epoxy compound, exhibiting high thermal conductivity, low thermal expansion and excellent electrical insulating properties. EP 140FR can be used with a variety of curing agents.

**Features & Benefits**

- High thermal conductivity
- Flexible pot life
- Excellent electrical properties
- Low viscosity
- High temperature resistance

**Applications**

Encapsulation of electrical and electronic devices and components, where high heat dissipation and low thermal expansion are needed

**Typical Uncured Properties**

**Note:** The following technical information and data should be considered representative or typical only and should not be used for specification purposes.

<b>Resin EP 140FR</b>	
<b>Appearance/Color</b>	Black
<b>Viscosity@25°C, mPa*s</b>	40000-60000
<b>Density@ 25°C, g/cm<sup>3</sup></b>	2.2-2.3
<b>Equivalent Weight (calc.), g/eq</b>	700-800

**Instructions for use:**

Warm EP 140FR to 40-50°C and stir contents thoroughly before withdrawing material.

Weigh required amount of resin and hardener into a clean container in the recommended ratio. Blend thoroughly being careful to scrape sides and bottom of the container for 3-4 minutes to ensure uniform mixture.

To produce a void-free casting the mixture should be deairing at 2-5 mmHg for 5-8 minutes to remove trapped air.

Pour the mixture into mold.

Preheating the mold reduces viscosity of the mixture and improves its flow.

Further deairing in the mold may be required.

## Technical Data: EP 140FR/ Hardeners EPC 124/ EPC 520/ EPC 304IP55

Issued: Nov.2011  
Revision 2: July 2018, Page: 2

**Note:** The following technical information and data should be considered representative or typical only and should not be used for specification purposes.

Processing	Resin EP 140FR	Hardeners		
		EPC 124	EPC 520*	EPC 304IP 55
	Mix Ratio, w/w	100:6.8-7.2	100:6.8-7.2	100:7.5-8.0
	Mix Viscosity@ 25°C, mPa*s	4000-7000	4000-7000	4000-7000
	Gel Time @ 25°C, (100g), min	50-70	120-150	150-180
	Typical Curing Schedule	24hr/RT	24hr/RT + 4hr/80°C	24hr/RT
Cured Properties**	HDT, °C	60	108	76
	Hardness, Shore D	90	90	90
	Tensile Strength, MPa	39	40	38
	Tensile Elongation, %	0.5-0.7	0.5-0.7	0.7-1.0
	Thermal Conductivity, W/m-K	0.7 – 0.8		
	Linear Shrinkage, %	0.2		
	Service Temperature, °C	-40÷ 130	-60÷ 160	-40÷ 130

\*) Post curing at 80-100°C is must.

\*\*) The samples were tested after post-curing 3hr at 120°C

### Storage

The shelf life of the EP 140FR is 12 months at 20-35°C.  
For the best results, store in tightly closed original containers.  
Certain resins and hardeners are susceptible to crystallization. If crystallization occurs, warm the container to 50-60°C until the crystals have dissolved. Stir and allow content to cool to room temperature before use.

### Packaging

Packaging sizes are available from 1L up to 18L pails.

**Limitation of Liability** Except where prohibited by law, Polymer-G and seller will not be liable for any loss or damage arising from the Polymer-G product, whether direct, indirect, special, incidental or consequential, regardless of the legal theory asserted, including warranty, contract, negligence or strict liability.

### Polymer Gvulot Ltd.

Kibbutz Gvulot, 85525 ISRAEL

Tel.: +972 (0)8 9987931, Fax.: +972 (0)8 9965286

Mail: [info@polymer-g.com](mailto:info@polymer-g.com)

<http://www.polymer-g.com>