

Technical Data:

Issued: November 2022
Revision 1: Nov. 2022, Page: 1

Resin EP 333LV/ Hardener EPC 9

Product Description

EP 333LV is a low viscosity self-extinguishing potting and encapsulating flame retardant epoxy compound. It displays high physical and electrical properties.

EP 333LV can be applied with various curing agents depending on customer requests.

Features & Benefits

- Low viscosity
- Flexible pot life
- Suitable for manual and automatic mixing
- Self-extinguishing UL-94 V-0 certified
- RT curing
- Excellent electrical properties

Applications

High voltage/High power electrical and electronic potting and encapsulation

Typical Uncured Properties

Note: The following technical information and data should be considered representative or typical only and should not be used for specification purposes.

Resin EP 333LV	
Appearance/Color	Black/Red/Gray
Viscosity@25°C, mPa*s	2500-3500
Density@ 25°C, g/cm³	1.50-1.54
Equivalent Weight (calc.), g/eq	435-450

Instructions for use

Stir compound EP 333LV thoroughly in the original container prior to use

Technical Data:

Issued: November 2022
Revision 1: Nov. 2022, Page: 1

Resin EP 333LV/ Hardener EPC 9

Note: The following technical information and data should be considered representative or typical only and should not be used for specification purposes.

Processing	Resin EP 333LV	Hardener, EPC 9
	Mix Ratio, w/w	100:8
	Mix Viscosity @ 25°C, mPa*s	2000-3000
	Pot life @ 25°C, min	10-15
	Gel Time @ 25°C, (100g), min	15-20
	Typical Curing Schedule	24hr/RT
Cured	Hardness, Shore D	85-90
Properties*	Tensile Strength, MPa	25-35
	Tensile Elongation, %	0.8-1.5
	Flexural Strength, MPa	40-80
	Flexural Module, MPa	2500-4000
	Service temperature, °C	-40 to 90
	Thermal Conductivity, W/m-K	0.38-0.42
	Flammability Rating	UL 94 -V-0

*) Results depend on time after curing.
High results are obtained after 7 days.

Storage Store products at 20-35°C for maximum shelf life.

Packaging Packaging sizes are available from 1L up to 18L pails.

Shelf Life These products have a shelf life of 12 months in their unopened original bulk containers.

Limitation of Liability Except where prohibited by law, Polymer-G and seller will not be liable for any loss or damage arising from the Polymer-G product, whether direct, indirect, special, incidental or consequential, regardless of the legal theory asserted, including warranty, contract, negligence or strict liability.