POLYMERIG

Technical Data: Issued: January 2022 Revision: January 2022, Page: 1	EP GP 30 Two-component Epoxy A	Adhesive	
Product Description	EP GP 30 is a two-component metals, wood, plastic materia resistance over a range of tem	ils and ceramics. El	
Features & Benefits	• Good adhesion properties	• Semi-flexible	
	• Thermal shock resistivity	• Easy to mix @ 1:1 ratio	
	• Good electrical properties	• VOC free	
Applications Typical Uncured Properties	Multipurpose structural adhesive. Note: The following technical information and data should be considered representative or typical only and should not be used for specification purposes.		
	typical only and should not		-
	typical only and should not Base Resins		-
		be used for specification p Base (A)	Epoxy Amines and Mercaptan
	Base Resins	be used for specification p Base (A) Hardener (B) Base (A)	Epoxy Amines and Mercaptan terminated polymer Clear to yellowish
	Base Resins Appearance/Color Viscosity @ 25°C, mPa*s	be used for specification p Base (A) Hardener (B) Base (A) Hardener (B) Base (A)	Epoxy Amines and Mercaptan terminated polymer Clear to yellowish Yellowish 11,500-13,500

Tel.: +972 (0)8 9987931, Fax.: +972 (0)8 9965286



Technical Data: Issued: January 2022 Revision: January 2022, Page: 2 **EP GP 30**

Two-component Epoxy Adhesive

Typical Cured
PropertiesNote: The following technical information and data should be considered representative or
typical only and should not be used for specification purposes.ColoramberTack-free time, @ 25°C, hr2-3Final curing @ 25°C, hr24Hardness, Shore D60-70Service Temperature, °C-30 to 90

Storage	Store products at 15-35°C for maximum shelf life.	
Packaging	50 ml 1:1 Duo-Pack cartridges	
Shelf Life	These products have a shelf- life of 12 months in their unopened original bulk containers and 12 months in Duo-Pack cartridges.	
Limitation of Liability	Except where prohibited by law, Polymer-G and seller will not be liable for any loss or damage arising from the Polymer-G product, whether direct, indirect, special, incidental or consequential, regardless of the legal theory asserted, including warranty, contract, negligence or strict liability.	