

**Technical Data: EP 140FR/ Hardeners EPC 124/ EPC 520/
EPC 304IP55**
Issued: Nov.2011
Revision 2: July 2018, Page: 1

Product Description EP 140FR is a highly filled potting and encapsulating epoxy compound, UL 94-V-0 approved, exhibiting high thermal conductivity, low thermal expansion and excellent electrical insulating properties. EP 140FR can be used with a variety of curing agents.

- Features & Benefits**
- High thermal conductivity
 - Excellent electrical properties
 - High temperature resistance
 - UL 94-V-0 approved
 - Low viscosity
 - Flexible pot life

Applications Encapsulation of electrical and electronic devices and components, where high heat dissipation and low thermal expansion are needed

Typical Uncured Properties **Note:** The following technical information and data should be considered representative or typical only and should not be used for specification purposes.

Resin EP 140FR	
Appearance/Color	Black
Viscosity@25°C, mPa*s	40000-60000
Density@ 25°C, g/cm³	2.2-2.3
Equivalent Weight (calc.), g/eq	700-800

Instructions for use: Warm EP 140FR to 40-50°C and stir contents thoroughly before withdrawing material.
 Weigh required amount of resin and hardener into a clean container in the recommended ratio. Blend thoroughly being careful to scrape sides and bottom of the container for 3-4 minutes to ensure uniform mixture.
 To produce a void-free casting the mixture should be deairing at 2-5 mmHg for 5-8 minutes to remove trapped air.
 Pour the mixture into mold.
 Preheating the mold reduces viscosity of the mixture and improves its flow.
 Further deairing in the mold may be required.

Technical Data:

Issued: Nov.2011
Revision 2: July 2018, Page: 2

**EP 140FR/ Hardeners EPC 124/ EPC 520/
EPC 304IP55**

Note: The following technical information and data should be considered representative or typical only and should not be used for specification purposes.

Processing	Resin EP 140FR	Hardeners		
		EPC 124	EPC 520*	EPC 304IP 55
	Mix Ratio, w/w	100:6.8-7.2	100:6.8-7.2	100:7.5-8.0
	Mix Viscosity @ 25°C, mPa*s	4000-7000	4000-7000	4000-7000
	Gel Time @ 25°C, (100g), min	50-70	120-150	150-180
	Typical Curing Schedule	24hr/RT	24hr/RT + 4hr/80°C	24hr/RT
Cured Properties**	HDT, °C	60	108	76
	Hardness, Shore D	90	90	90
	Tensile Strength, MPa	39	40	38
	Tensile Elongation, %	0.5-0.7	0.5-0.7	0.7-1.0
	Thermal Conductivity, W/m-K	0.7 – 0.8		
	Linear Shrinkage, %	0.2		
	Service Temperature, °C	-40÷ 130	-60÷ 160	-40÷ 130

*) Post curing at 80-100°C is must.

**) The samples were tested after post-curing 3hr at 120°C

Storage

The shelf life of the EP 140FR is 12 months at 20-35°C.
For the best results, store in tightly closed original containers.
Certain resins and hardeners are susceptible to crystallization. If crystallization occurs, warm the container to 50-60°C until the crystals have dissolved.
Stir and allow content to cool to room temperature before use.

Packaging

Packaging sizes are available from 1L up to 18L pails.

Limitation of Liability

Except where prohibited by law, Polymer-G and seller will not be liable for any loss or damage arising from the Polymer-G product, whether direct, indirect, special, incidental or consequential, regardless of the legal theory asserted, including warranty, contract, negligence or strict liability.