

**Technical Data:** 

Issued: July 2008

Revision 3: Sept. 2022, Page: 1

### U 105

Soft, Two Component PBD-based PU Compound offering exceptional hydrolytic stability and very low glass transition

### **Product Description**

U 105 is a two-component, unfilled, soft, potting, casting and encapsulating PU compound. It has excellent thermal cycling properties and hydrolytic stability, extremely low glass transition temperature and low water permeability.

#### **Features & Benefits**

- High flexible
- High hydrolytic stability
- Low moisture permeability
- High thermal cycling resistivity

• Low Tg

• Excellent electrical properties

### **Applications**

Electrical and electronic potting and encapsulation

## Typical Uncured Physical Properties

Note: The following technical information and data should be considered representative or typical only and should not be used for specification purposes.

Base Resins	U 105 (A) UC 138 (B)	PBD Isocyanate
Appearance/Color	U 105 (A) UC 138 (B	Black Amber
Viscosity @ 25°C, mPa*s per ASTM-D-2393	U 105 (A) UC 138 (B	1800-2200 150-250
<b>Density</b> @ 25°C, g/cm <sup>3</sup>	U 105 (A) UC 138 (B	0.95 1.2
Mix Ratio A:B (w/w)	100:10	
Mix Viscosity@ 25°C, mPa*s per ASTM-D-2393	1300-1700	
<b>Gel-time</b> @ 25°C, 100g, min	90-120	
Final curing @ 25°C, days	6-8	

**Instructions for use:** 

Stir compound U 105 thoroughly in the original container prior to use

Tel.: +972 (0)8 9987931, Fax.: +972 (0)8 9965286

Mail: <a href="mailto:info@polymer-g.com">info@polymer-g.com</a> <a href="http://www.polymer-g.com">http://www.polymer-g.com</a>



### **Technical Data:**

Issued: July 2008 Revision 3: Sept. 2022, Page: 2

## U 105

Soft, Two Component PBD-based Polyurethane Compound offering exceptional hydrolytic stability and very low glass transition

# Typical Cured Properties

Note: The following technical information and data should be considered representative or typical only and should not be used for specification purposes.

Color	black
Hardness, Shore A (after 7 days)	36-38
Glass transition temperature, °C	-78
Service Temperature, °C	-55 to 90
Water Absorption @25°C, 7 days, %	0.15-0.20

Storage	Store products at 15-35°C for maximum shelf life.	
Shelf Life	These products have a shelf- life of 9 months in their unopened original bulk containers.	
Packaging	Packaging sizes are available from 1L up to 200L barrel.	
Limitation of Liability	Except where prohibited by law, Polymer-G and seller will not be liable for any loss or damage arising from the Polymer-G product, whether direct, indirect, special, incidental or consequential, regardless of the legal theory asserted, including warranty, contract, negligence or strict liability.	

Tel.: +972 (0)8 9987931, Fax.: +972 (0)8 9965286

Mail: <u>info@polymer-g.com</u> http://www.polymer-g.com