

Technical Data:

Issued: July 2008

Revision 3: February 2023, Page: 1

U 205

Two-Component Self-extinguishing Soft PBD-based PU Compound

Product Description

U 205 is a two-component flame retardant, soft, potting and encapsulating PU compound. U 205 has excellent thermal cycling properties and hydrolytic stability, low glass transition temperature and low water permeability.

Features & Benefits

- High flexible
- Low moisture permeability
- Low Tg
- Self-extinguishing UL certified
- High thermal cycling resistivity
- Excellent electrical properties

Applications

Electrical and electronic potting and encapsulation

Typical Uncured Properties

Note: The following technical information and data should be considered representative or typical only and should not be used for specification purposes.

Base Resins	U 205 (A) UC 138 (B)	PBD Isocyanate
Appearance/Color	U 205 (A) UC 138 (B)	Black Amber
Viscosity @ 25°C, mPa*s per ASTM-D-2196	U 205 (A) UC 138 (B)	2000-4000 150-250
Density @ 25°C, g/cm³	U 205 (A) UC 138 (B)	1.26 ± 0.03 1.20 ± 0.02
Mix Ratio A:B (w/w)	100:10	
Mix Viscosity @ 25°C, mPa*s per ASTM-D-2196	1500-2500	
Gel-time @ 25°C, min	50-90	
De-mold time @ 25°C, hr	7-8	
Ultimate cure, days	6-8	

Instructions for use:

Stir compound U 205 thoroughly in the original container prior to use

Polymer Gvulot Ltd.

Kibbutz Gvulot, 85525 ISRAEL

Tel.: +972 (0)8 9987931, Fax.: +972 (0)8 9965286

Mail: info@polymer-g.com

<http://www.polymer-g.com>

Technical Data:

Issued: July 2008

Revision 3: February 2023, Page: 2

U 205

Two-Component Self-extinguishing Soft PBD-based PU Compound

Typical Cured Properties

Note: The following technical information and data should be considered representative or typical only and should not be used for specification purposes.

Color	Black
Hardness, Shore A	25-45
Service Temperature, °C	-40 to 90
Flammability Rating, UL certified	UL 94 -V-0

Storage

Store products at 15-30°C for maximum shelf life.

Packaging

Packaging sizes are available from 1L up to 18L pails.

Shelf Life

These products have a shelf- life of 6 months in their unopened original bulk containers.

Limitation of Liability

Except where prohibited by law, Polymer-G and seller will not be liable for any loss or damage arising from the Polymer-G product, whether direct, indirect, special, incidental or consequential, regardless of the legal theory asserted, including warranty, contract, negligence or strict liability.