

#### **Technical Data:**

Issued: Sept. 2005 Revision 2: May 2018, Page: 1

### U 233

Two-Component Low Viscosity Potting and Casting Semi-flexible Polyurethane Compound

#### **Product Description**

U 233 is a two-component, low viscosity, semi-flexible PU compound for potting, casting and encapsulating. U 233 exhibits good mechanical and electrical properties. Pot life can be varied in wide range upon customer request.

#### **Features & Benefits**

- Flexible pot life
- Semi-flexible
- Good adhesion to metals and ceramics
- High electrical and mechanical properties
- Suitable for manual and automatic mixing

#### **Applications**

Electrical and Electronic Potting and Encapsulating

#### **Typical Uncured Physical Properties**

Note: The following technical information and data should be considered representative or typical only and should not be used for specification purposes.

| Base Resins                                | U 233 (A)<br>UC 138 (B) | Polyol mixture<br>Isocyanate     |
|--|-------------------------|----------------------------------|
| Appearance/Color                           | U 233 (A)<br>UC 138 (B) | Transparent/Black<br>Amber       |
| Viscosity @ 25°C, mPa*s<br>per ASTM-D-2393 | U 233 (A)<br>UC 138 (B) | 400-700<br>150-250               |
| <b>Density</b> @ 25°C, g/cm <sup>3</sup>   | U 233 (A)<br>UC 138 (B) | $1.05 \pm 0.02 \\ 1.20 \pm 0.02$ |
| Mix Ratio A:B (w/w)                        | 100:45                  |                                  |
| Mix Viscosity@ 25°C, mPa*s per ASTM-D-2393 | 300-500                 |                                  |
| Pot life@ 25°C, 100g, min                  | 15-20                   |                                  |
| <b>Gel-time</b> @ 25°C, (100g), min        | 25-35                   |                                  |
| Curing time @ 25°C, hr                     | 24                      |                                  |

#### **Instructions for use:**

Stir compound U 233 thoroughly in the original container prior to use

http://www.polymer-g.com

Tel.: +972 (0)8 9987931, Fax.: +972 (0)8 9965286



#### **Technical Data:**

Issued: Sept.2005 Revision 2: May 2018, Page: 2

## U 233

Two-Component Low Viscosity Potting and Casting Semi-flexible Polyurethane Compound

# Typical Cured Properties

Note: The following technical information and data should be considered representative or typical only and should not be used for specification purposes.

| Color                             | Off-White/Black |
|-----------------------------------|-----------------|
| Final properties @ 25°C, days     | >7              |
| Hardness, ASTM -D-2240, Shore A   | 90-95           |
| Tensile Strength, ASTM-D-638, MPa | 8-10            |
| Tensile Elongation, ASTM-D-638, % | 60-70           |
| Service Temperature, °C           | -40 to 90       |

| Storage                 | Store products at 15-30°C for maximum shelf life.   |  |
|-------------------------|---|--|
| Packaging               | Packaging sizes are available from 1L up to 5L jerricans.   |  |
| Shelf Life              | These products have a shelf- life of 9 months in their unopened original containers.  |  |
| Limitation of Liability | Except where prohibited by law, Polymer-G and seller will not be liable for any loss or damage arising from the Polymer-G product, whether direct, indirect, special, incidental or consequential, regardless of the legal theory asserted, including warranty, contract, negligence or strict liability. |  |

Tel.: +972 (0)8 9987931, Fax.: +972 (0)8 9965286

http://www.polymer-g.com